



TECHNICAL DATA SHEET

KEIM BIOSIL®

1. PRODUCT DESCRIPTION

KEIM Biosil is a ready-to-use silicate paint for interior use according to DIN EN 13 300 (also fulfils the requirements of DIN 18363 para. 2.4.1 silicate emulsion paint). KEIM Biosil is awarded with Cradle to Cradle Certified® Silver and C2C Certified Material Health Certificate™ Gold.

2. FIELD OF APPLICATION

KEIM Biosil is suitable for all common interior wall and ceiling surfaces, e.g. in offices, living rooms, bedrooms, kitchens, bathrooms and basements. It is particularly suitable KEIM Biosil for sensitive areas such as hospitals, nursery schools or schools and also for rooms where food is stored. Highly absorbent or sanding substrates are pre-treated with KEIM Granital-Dilution. In the case of white coats on gypsum plasterboard surfaces or surfaces with gypsum stain filler, a primer coat of KEIM Grundierweiss (Ecosil-Grund) is beneficial. KEIM Grundierweiss (Ecosil-Grund) should not be used on pure gypsum plasters (P IV a,b and P Va). In this case, coatings with KEIM Ecosil-ME or KEIM Optil are recommended.

Not suitable for:
substrates with salt efflorescences; lacquered surfaces; wood substrates

3. PRODUCT PROPERTIES

- good covering power
- suitable for allergy sufferers
- suitable for food products
- low stress
- low environmental impact
- Cradle to Cradle Certified®-Certificate Silver
- C2C Certified Material Health Certificate™ Gold
- permeable
- anti-fungal and anti-algae thanks to natural alkalinity
- scrub-resistant
- fire behaviour: non-flammable (Class A2-s1,d0 as per EN 13501-1 acc. to classification report)
- no solvents added
- no plasticisers added
- no preservatives added

MATERIAL CHARACTERISTICS:

- Density: approx. 1,4 - 1.6 g/cm³
- Organic content: < 5 %
- pH value: approx. 11

CLASSIFICATION:

- Classification according to: DIN EN 13300
- Classification according to VOB: Silicate emulsion paint according to DIN 18363 sec. 2.4.1
- Water vapour diffusion current density (V-value): > 2000 g/(m² · d)
- Diffusion-equivalent air layer thickness (sd-value): < 0,01 m
- Wet abrasion resistance: Class 2

TECHNICAL DATA SHEET – KEIM BIOSIL®

- Test standard Wet Abrasion Resistance:	EN ISO 11998
- Contrast ratio (covering power):	Class 1
- Ergiebigkeit zum Kontrastverhältnis (Deckvermögen):	7 m ² /l
- Test standard Hiding power:	ISO 6504-3
- Gloss level at 85°:	dull matt
- Test standard Gloss level:	ISO 2813
- Maximum particle size:	fine
- Test standard Maximum particle size:	EN 1524

COLOUR SHADES:

White, colour shades only with pure mineral lightfast pigments. KEIM Biosil can be tinted with KEIM PPF-Technology® according to all common colour collections. Please always check the colour for correctness before application. Only use colour shades from one tinting batch within a surface. On-site tinting exclusively with KEIM colour concentrates.

COMPOSITION:

Full declaration in compliance with the "natureplus®" award guideline:

Silicate and calcite fillers, potassium silicate, water, titanium dioxide, styrene acrylic resin, water repellents, thickeners, stabilisers, wetting agents, defoamers. Origin of mineral fillers: Germany and/or Austria.

4. APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION:

The substrate must be sound, solid, dry, clean and free from dust and grease. On clay plasters, pretreatment with KEIM Granital-Dilution, diluted 1:1 with water, is recommended. The base coat is to be diluted with 10 % water, top coat undiluted. Optimisation of the surface homogeneity of the subsequent coats, especially under difficult lighting conditions, can be achieved by pre-treatment with KEIM Granital-Dilution. In case of glancing light conditions, ensure adequate substrate preparation, suitable tools and increased care during application.

APPLICATION CONDITIONS:

Ambient and substrate temperature during application and drying must be ≥ 5 °C.

PREPARATION OF MATERIAL:

Stir up KEIM Biosil thoroughly before application.

APPLICATION:

KEIM Biosil can be brushed, rolled or sprayed (nozzle ≥ 423). (Recommendation for smooth substrates, e.g. plasterboard: short-floor roller).

Primer coat: Apply KEIM Biosil undiluted or diluted with 10 % of Wasser.

Final coat: Apply KEIM Biosil undiluted.

DRYING TIME:

Can be overcoated after 6 hours at the earliest (at 23 °C and 50% RH). At higher relative humidity, layer thicknesses and/or lower temperatures, drying is delayed accordingly.

CONSUMPTION:

approx. 0,11 l/m² for a single coating.

These material consumption values are guide values for smooth substrates. Exact consumption values must be determined by means of test areas.

CLEANING OF TOOLS:

Clean immediately with water.

5. PACKAGING

Container content	Unit of measure	Quantity on pallet	Type of container
12.5	l	32	bucket
5	l	70	bucket
2.5	l	80	bucket

6. STORAGE

max. storage time	Storage conditions
12 months	protected from heat and direct sun. frost-free keep container tightly sealed. cool

7. DISPOSAL

For disposal information refer to section 13 of the safety data sheet.

EC WASTE CODE:

Waste code: 08 01 12

8. SAFETY INSTRUCTIONS

Please, refer to the Material Safety Data Sheet.

The paint is formulated without the addition of preservatives. Medium and intensive colour shades may contain traces of pot preservatives.

9. GENERAL INFORMATION

Cover surfaces not to be treated, especially glass, ceramics and natural stone. Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water.

Mixing with products not part of the system or other foreign additives is not permitted.

10. CERTIFICATES & QUALITY SEALS

TECHNICAL DATA SHEET – KEIM BIOSIL®



The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.



KEIM MINERAL PAINTS LTD

Santok Building / Deer Park Way, Donnington Wood / Telford / Shropshire TF2 7NA
Tel. +44 1952 231 250 / Fax +44 1952 231 251
www.keim.com / sales@keimpaints.co.uk